



PRODUCT INFORMATION

Hollow Ceramic Microspheres

Standard Grades

Introduction

Fillite is a glass hard, inert, hollow silicate sphere. Fillite is primarily used to reduce the weight of plastics, rubbers, resins, cement, etc., but also imparts further benefits in many situations. Many of the advantages from the use of Fillite, including increased filler loading and improved rheology, are directly attributed to the spherical nature of the material.

Characteristics

- Lightweight
- Free-flowing
- Off-White in Colour
- Spherical
- Inert

Typical Applications

Refractories, PVC flooring, oilwell cements, brake linings, Phenolics, Epoxies, Cast Polyesters, synthetic marbles, syntactic foams, BMC, SMC and FRP. Low density cements, shotcrete and gypsum board joint compounds. Automotive sound-dampening sheets.

Advantages

Reduced weight, increased filler loadings, better flow characteristics, less shrinkage and warping. Improved physical properties in moldings, castings and laminates, reduced water absorption, improved flame retardance, improved chemical resistance.

Chemical Properties

Shell	Al ₂ O ₃	27%-33%
	SiO ₂	55%-65%

	Fe ₂ O ₃	6% maximum
Gas	Carbon Dioxide	70%
	Nitrogen	30%

Physical Properties

Average Particle Density	0.6-0.85 g/cc (44lbs/ft ³)
Average Bulk Density	0.35-0.45 g/cc (25lbs/ft ³)
Packing Factor	60%-65%
Hardness	Mohs Scale 5
Average Wall Thickness	5%-10% Sphere Diameter
Melting Temperature	1200°-1350°C (2190°-2460°F)
Thermal Conductivity	0.11 Wm ⁻¹ K ⁻¹
Loss on Ignition	2% maximum
Surface Moisture	0.3% maximum
Crush Strength	105-210 kg/cm ² (1500 - 3000 psi)
Oil Absorption	16-18g oil/100g

Grades

	SG (500)	52/7S FG (355) (300)	PG (300LF)	160	106	
Particle Size Range (microns)	5-500	5-355	5-300	5-500	5-160	5-106
Particle Size Distribution						
% Passing 500 microns	100	100	100	100	100	100
% Passing 300 microns	85-100	95-100	99.5-100	97-100	100	100
% Passing 180 microns	--	--	--	--	99.5-100	--
% Passing 150 microns	40-80	40-80	40-80	40-60	--	100
% Passing 106 microns	25-55	25-55	25-55	15-30	40-80	99.7-100
% Passing 50 microns	2-10	5-10	5-10	2-10	10-20	15-30

Other than a representation that the products sold by Trelleborg Fillite Ltd and/or Trelleborg Fillite Inc will, on average, meet the criteria set forth above, which is and shall be subject to confirmation by the purchaser, Trelleborg Fillite Ltd and/or Trelleborg Fillite Inc makes no warranty, guarantee or representation of any kind, express or implied, and specifically EXCLUDES any and all WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Trelleborg Fillite Ltd and/or Trelleborg Fillite Inc will not be liable for consequential damages and under no circumstances will Trelleborg Fillite Ltd and/or Trelleborg Fillite Inc's liability exceed the price paid for non-conforming product by its customers.