


**CUROX® M-302**

## Technical Data Sheet - Thermosets Ketone peroxides (Ambient temperature)



Chemical Name	Methylethyl ketoneperoxide
CAS-No.	1338-23-4
Properties	Liquid mixture

**Description**

Colourless, mobile liquid, consisting of peroxides based on methyl ethyl ketone, essentially desensitised with aliphatic ester. This ketone peroxide is used as an initiator (radical source) in the curing of unsaturated polyester resins. Main application: curing of moulded parts at ambient temperature in combination with cobalt accelerators.

Technical Data	
Property	Characteristics / Value
Appearance	colourless liquid
Active oxygen	approx. 9.5 % w/w
De-sensitising agent	aliphatic ester
Density at 20°C	approx. 1,02 g/cm <sup>3</sup>
Viscosity at 20°C	approx. 13 mPas
Miscibility	immiscible with water, miscible with ester, UP/VE-resins
Critical temperature (SADT)	approx. 60 °C
Cold storage stability	liquid to below -25 °C
Recommended storage temperature	below 30 °C
Storage stability (activity) as from date of delivery	6 months

**CUROX® M-302**

## Technical Data Sheet - Thermosets Ketone peroxides (Ambient temperature)

**Further Data****Application****POLYESTER CURING:**

Standard curing agent for all UP resin types at ambient temperature in combination with cobalt accelerators. Standard dosage level: 1-3% as supplied, with 0.2-2% of a 1% cobalt solution.

"Shelf life" (gel time of resin + peroxide) usually only a few hours, depending on temperature and resin type. "Pot life" (gel time of resin + peroxide + accelerator) relatively short, but may be prolonged by adding Inhibitor TC-510. Thus, the mould release factor (fMR = tMR/tgel) can be improved considerably.

**CURING PERFORMANCE:**

Moderate evolution of heat. Relatively long mould release time, moderate mould release factors. Temperatures below 20°C prolong curing times considerably, alternatively cobalt / amine accelerators should then be used.

**PROCESSING METHODS:**

Particularly hand lay-up, spray lay-up, centrifugal casting, filament winding, casting of resins, and surface coatings (putties, fillers, gelcoats and topcoats).

**SPRAY EQUIPMENT:**

Use spray equipment in accordance with manufacturer's instructions. Ensure all safety devices are operational. Do not clear gun by spraying MEKP into the air.


## CUROX® M-302

### Technical Data Sheet -Thermosets Ketone peroxides (Ambient temperature)

#### Further Data

#### Activity:

"Cobalt Curing" after DIN 16945 at 25°C with OPA resin (20g in a test tube)						
Formulation (parts by weight)						
Medium reactive resin type (OPA)	100	100	100	100	100	100
CUROX® M-302	2	2	2	2	1	1
Accelerator C-101	2	1	0.5	0.2	1	0.5
Curing data						
Gel time $t_{gel}$ [min]	1.5	2.5	5.0	19.5	6.0	12.5
Curing time $t_{max}$ [min]	15.0	16.0	20.5	45.5	34.0	51.5
Peaktemperature $T_{max}$ [°C]	141	143	139	112	107	88





**UNITED INITIATORS**

*driving your success*

## **CUROX® M-302**

Technical Data Sheet -Thermosets Ketone peroxides (Ambient temperature)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Product Information

25.02.2009

UI 5019

Page 4/4